

# MH-W58HM

## Face Material

weight	thickness	material
100g / m <sup>2</sup> ± 10% ISO536	120μ ± 10% ISO534	Beige paper

## Liner

60g / m <sup>2</sup> ± 10% ISO536	53μ ± 10% ISO534	Super calendered semi-gloss white glassine liner
-----------------------------------	------------------	--------------------------------------------------

## Adhesive

HM is a permanent, rubber-based adhesive. This is an adhesive with a medium initial viscosity. It has excellent adhesion performance on non-polar surfaces; and has a certain degree of softness, which can be used for indirect to food, direct contact labeling of advertising stickers and cosmetics.

## Peel adhesion

initial adhesion 13 N/25mm FTM 9 st.st	20 minutes Peel adhesion value on steel at 90 angle 10 N/25mm FTM 2 st.st	24 hours Released forced value on steel at 90 angle 11 N/25mm FTM 2 st.st
-------------------------------------------	---------------------------------------------------------------------------------	---------------------------------------------------------------------------------

## Temperature

Min. Appl. Temp. 8°C	Service Temp. -5°C to 60°C (24H after labeling)
----------------------	-------------------------------------------------

## Applications

Typically it is used to make label on red wine, food, etc.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

## Printing Methods

Avoid material deformation caused by overheating. It can be applied to various printing methods such as flexographic printing, letterpress printing and screen printing, and has good expressiveness to ink.

## Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.