

# FHPP50RP-PEK83HM

## Face Material

weight	thickness	material
65 ± 10%g/m <sup>2</sup> ISO 536	0.045 ± 10%mm ISO 534	Holographic PP with point printing

## Liner

80 ± 10%g/m <sup>2</sup> ISO 536	0.8 ± 10%mm ISO 534	Single-color plastic-coated yellow PEK release paper
----------------------------------	---------------------	--

## Adhesive

A general permanent rubber adhesive. HM is an adhesive with a high initial viscosity. It has excellent adhesion performance on non-polar surfaces; and has a certain degree of softness, which can be used for direct contact labeling of food, advertising stickers and cosmetics.

## Peel adhesion

Initial adhesion 10N/25mm FTM 9 st.st	20 minutes Peel adhesion value on steel at 180° 16N/25mm FTM 1 st.st	20 minutes Peel adhesion value on steel at 90° 8N/25mm FTM 2 st.st
--	--	--

## Temperature

Min. Appl. Temp. 8°C	Service Temp. -5°C+60°C (after 24hrs)
----------------------	---------------------------------------

## Applications

The product has certain tear resistance, dimensional stability and chemical corrosion resistance, and is suitable for making various labels.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

## Printing Methods

The surface has been treated with a special coating, which can meet various printing methods. It is recommended to die-cut with a high-hardness tool, and at the same time avoid label overflow due to excessive winding tension. Provides excellent stiffness and clarity, good printability and die-cutting properties, excellent chemical and UV resistance.

## Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.