

# FWMCPP80-W80AD

## Face Material

weight	thickness	material
80g / m <sup>2</sup> ± 10% ISO536	0.08mm ± 10% ISO534	Biaxially stretched white calendered polypropylene film with special coating on the surface

## Liner

weight	thickness	material
80g / m <sup>2</sup> ± 10% ISO536	0.065mm ± 10% ISO534	white glassine paper with super calender treatment

## Adhesive

AD is a removable adhesive. This is a medium and high viscosity adhesive for wet tissue paper. Good chemical resistance and UV resistance, suitable for large packaging and high humidity applications. It can be used for non-direct contact labeling of cosmetics and other products.

## Peel adhesion

initial adhesion	20 mins Peel adhesion value on steel at 180 angle	20 mins Peel adhesion value on steel at 90 angle
6 N/25mm or tear off FTM9	3 N/25mm or tear off FTM1	2N/25mm or tear off FTM2

## Temperature

Min. Appl. Temp. 5 °C	Service Temp. -20°C +60°C (24H after labeling)
-----------------------	--

## Applications

The material has certain tearing and chemical corrosion resistance, moderate temperature resistance, stable physical and chemical properties, good transparency, and a certain barrier property. It has the removable property of repeated pasting on many objects to be pasted. It is widely used to make tissue bag sealing stickers and wet tissue paper sealing stickers. Due to the different surface properties of the objects to be pasted, it is recommended to conduct label pasting test on the objects to be put into use.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

## Printing Methods

Polypropylene film with high density and no wrinkle after repeated pasting has good die-cutting and overprinting performance and high tear resistance. The surface has a layer of transparent coating. Avoid material deformation caused by overheating. It can be used for flexographic printing, letterpress printing, screen printing and other printing methods, and has good performance on ink. Product labels with important properties such as water resistance, oil resistance and chemicals.

### Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.